

PT. ANUGERAH MANDIRI WATERF

CONPLAST WP421

Packaging

Conplast WP421 is supplied in 20 liter pails or 210 liter drums.

Storage

Conplast WP421 has a minimum shelf life of 12 months provided the temperature is kept within the range 2⁰c to 50⁰c.

Precautions

Health and safety

Conplast WP421 is slightly toxic and must not be ingested. It is mildly alkaline and prolonged contact with the skin must be avoided, splashes to the skin should be removed with water. In the event of splashes to the eyes should be washed immediately with plenty of water and seek medical advice.

Additional information

Technical data and guidance can be provided on a wide range admixtures and concreting aids including accelerators, plasticisers, air entraining agents, waterproofer, mould release agents, surface retarders, workability aids, grouts and repair materials.

* See separate data sheet

Table

Admixture	Cement Type I (kg/m ³)	Fine Aggregate (kg/m ³)	Coarse Aggregate 10/20 (kg/m ³)	Free Water (ltrs/m ³)	Compressive Strength		Penetration DIN 1048 28 days
					7 days kg/cm ²	28 days kg/cm ²	
Control	360	780	1030	200	285	410	4.75 cm
Conplast WP421	360	780	1030	160	376	520	2.2 cm

PT. Fosroc Indonesia

Jl. Akasia II Blok A8 No.1
Delta Silicon Industrial Park
Lippo Cikarang
Bekasi 17550
Indonesia

telephone:
+ 62 21 897 2103

fax:
+ 62 21 897 2107

email:
indonesia@fosroc.com

Registered Office: Jl. Akasia II Blok A8 No.1, Delta Silicon Industrial Park, Lippo Cikarang, Bekasi 17550, Indonesia