



# Proofex Torchseal 3PV

## Prefabricated torch applied waterproofing membrane

### Description

Proofex Torchseal 3PV is a prefabricated, torch applied waterproofing membrane composed on selected, modified bitumen reinforced with polyester which gives good waterproofing properties.

### Uses

Proofex Torchseal 3PV can be used as conjunction element or **continuity, uniforming, waterproofed layer or vapour retarder** of the following areas:

- easements
- **Concrete roofs**
- Floor slabs
- Carpark
- Tunnels and subways
- **Concrete retaining structure**

### Properties

Proofex Torchseal 3PV is composed from modified bitumen with non-woven polyester mat reinforcement.

Characteristic	Value	
Width (m)	1 ± 10/100	
Weight (kg/m <sup>2</sup> )	1 ± 10/100	
Reinforcement 180 gr/m <sup>2</sup>	3 ± 10% with <b>non-woven</b> spun bond polyester mat	
Tensile strength (N/5cm)	Longitudinal	ASTM 0146 820
	Transversal	600
Elong@ break(%)	Longitudinal	ASTM 0146 50
	Transversal	60
Low temperature flexibility	-5°C to -10°C No cracking	
Water lightness	ASTM E96	Absolutely Impermeable
Softening point	ASTM D146	> 150°C

## Application

Prepare all tools and equipment to apply Proofex Torchseal membrane (propane gas torch with gas cylinder, a knife for cutting the membrane and a trowel with a rounded tip).

Use of protective gloves and goggles is highly recommended when applying with gas torch.

The concrete surface to be waterproofed should be free of dust, dirt and any other contaminants. Porous substrate should be coated with Fosroc recommended primer at an application rate of 200 - 800 gsm/m<sup>2</sup> or according to the porosity of the surface. The placement of Proofex Torchseal 3PV membrane, **used as waterproofing overlays, varies according to the nature** of the support, the slope and the duty. The bonding of the sheet, as well as their fastening to the support, is done by melting the waterproofing compound with propane gas torch burner.

Sheet must be firstly placed on to the support and then aligned by overlapping the edges by 10 cm on the sides and 15 cm on the top. While welding the joints, a part of the compound must now and cross the junction line.

Laying process of the waterproofing membrane should be stopped in case of rain, snow, fog and when the temperature is lower than 5°C.

## Packing, size and storage

Proofex Torchseal 3PV is available in rolls of 1 X10 m. Natural slate upper side finishing is also available on request.

Proofex Torchseal 3PV should be stored vertically in well aerated shelter. Protect against bad weather conditions and from extremely high temperature. Avoid stacking or overlapping of loose rolls / pallets.

## Safety

Proofex Torchseal 3PV does not contain any dangerous substance, coal tar or asbestos material.

