



SikaBond® NV

PVA Bonding Agent

Description	A polyvinyl acetate emulsion bonding agent It is added to cement to increase the bond strength between old and new concrete. SIKABOND NV is compatible with all types of Portland cement including Sulphate Resisting cement, high alumina cement and gypsum plaster.
Uses	As bonding agent for concrete, mortars, ceramic tiles, wood and insulation boards Suitable for use in concrete repair
Advantages	<ul style="list-style-type: none"> ■ Increased adhesive – cementitious mixes. ■ Better workability. ■ Easy to dilute. ■ Improves plasticity. ■ Reduces porosity and cracking.
Dosage	Added to the mixing water within the range 1 : 1 – 1 : 3 (depending on type of application)
Instruction for Use	
Surface Preparation	The substrate must be sound, clean and free of dust and loose particles. All cement laitance, oil, grease, dirt, etc., must be removed by using wire brush or other method
Application	<p>Bonding of new concrete to old concrete All the old concrete surfaces should be saturated with water Apply bonding coat by mixing cement with SIKABOND NV : water = 1 : 1 to a slurry consistency Then the lay the new concrete while the bonding is still tacky</p> <p>As a plaster bonding agent and cement rendering. Seal the surface and prime with slurry of SIKABOND NV : water = 1:1 add with Cement Then plaster or render while the bonding is still tacky</p> <p>Suggested mixes : Rendering for rough coat (thickness 10-30 mm) Mix cement : clean sand = 1 : 3, gauged to a stiff consistency with SIKABOND NV : water = 1 : 3</p> <p>Rendering for finishing coat (thickness 0-2 mm) Mix cement with SIKABOND NV : water = 1 : 1, to a trowellable consistency</p> <p>As a bonding agent for ceramic tile, mosaic</p> <ul style="list-style-type: none"> ■ Dampen the substrate as well as the tiles ■ Apply a bonding slurry with a solution of SIKABOND NV : cement = 1:1 to the damp substrate and to the back of tiles and allow to become tacky, then plaster the tile with mortar in required thickness and firmly press to the floor or wall to ensure full contact.



Limitations	Do not use SIKABOND NV as bonding coat without adding cement. Do not use SIKABOND NV in the structure that permanently in wet condition e.g. swimming pool. In this case use Sika Latex or Sika Top 77 D instead
--------------------	---

Technical Data

Type	Polyvinyl Acetate Emulsion
Colour	White
Specific Gravity	Approx 1.0 kg / ltr
Shelf life	Minimum 1 year if stored in original unopened container
Storage	Dry, cool, shaded place
Packaging	10 kg can 200 kg drum

Handling Precautions	<ul style="list-style-type: none"> ■ Avoid contact with skin and eyes ■ Wear protective gloves and eye protection during work ■ If skin contact occurs, wash skin thoroughly ■ If in eyes, hold eyes open, flood with warm water and seek medical attention without delay
-----------------------------	---

Legal Notes

The information and in particular the recommendations relating to the application and end-use of Sika products are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sales and delivery. Users should always refer to the most recent issue of the technical Data Sheet for the product concerned, copies of which will be supplied on request.



PT. ANUGERAH MANDIRI WATERPROOF

Office | Marketing
 Jl. Raya Bangkingan No.06
 Lakarsantri
 Surabaya, Jawa Timur, Indonesia 60214
 Telepon
 (031) 7673 - 911
 (031) 7670 - 735
 (031) 7672 - 945



PT. Sika Indonesia
 Jl. Raya Cibinong- Bekasi km. 20
 Limusunggal- Cileungsi
 BOGOR 16820- Indonesia
 Tel. +62 21 8230025
 Fax +62 21 8230025
 www.sika.co.id
 e-mail: marketing@sika.co.id

Branches
 Surabaya,
 Tel : 031-8690202
 Fax : 031-8682123
 Medan,
 Tel : 061-7941200
 Fax : 061-7940822
 Batam,
 Tel : 0778-424928,
 Fax : 0778-426913

Sub Distributor
 Bandung, Tel : 022-5423855,5423857, Fax : 022-5423517
 Denpasar, Tel : 0361-235998 – 235973, Fax : 0361-237053
 Makassar, Tel : 0411- 859147 – 858527, Fax : 0411-858527
 Balikpapan, Tel : 0542-411258 Fax : 0542-412230
 Pekanbaru, Tel : 0761-46993 – 47677, Fax : 0761-45112
 Duri/Dumai. Tel : 0765-595259 Fax : 0765-91135
 Palembang, Tel : 0711-351523 Fax : 0711-369858
 Palu, Tel : 0451-454855 – 422122, Fax : 0451-454855
 Manado, Tel /Fax : (0431) 324069

